

# ELECTRODE COAL TAR PITCH



PRODUCT OF THE UKRAINE

This product is from a Valetime Integrated Source

## SPECIFICATION

### Specification:

### GOST 10200-83

Grade 1	Grade 2	Grade 3	Grade 4
---------	---------	---------	---------

Softening temperature, °C	65-70	67-73	72-76	85-90
Mass fraction of substances, indissoluble in toluene, %, not less	24-28	25-31	26-31	31
Mass fraction of substances, indissoluble in quinoline, %, not over	7	8	10	12
Volatile products yield, %	59-63	58-62	Not over 59	53-57
Ash content, %, not over	0.3	0.3	0.3	0.3
Water mass fraction in resin, %, not over	4.0	4.0	4.0	4.0

### Disclaimer for Specifications