

ELECTRODE PITCH COKE



PRODUCT OF THE UKRAINE

This product is from a Valetime Integrated Source

SPECIFICATION

Specification:

GOST 3213-91

| Extra class | First class | Grade 2 | Grade 3 |
|-------------|-------------|---------|---------|
|-------------|-------------|---------|---------|

| | | | | |
|---|----------------------|----------------------|----------------------|----------------------|
| Ash content, not over, % | 0.25 | 0.30 | 0.30 | 0.50 |
| Total sulfur mass fraction, not over, % | 0.25 | 0.30 | 0.70 | 0.70 |
| Total humidity mass fraction, not over, % | 3.0 | 3.0 | 3.0 | 3.0 |
| Coal-volatile products yield, not over, % | 0.8 | 0.8 | 0.8 | 0.8 |
| Mass fraction of pieces less than 25mm, not over, % | 9.0 | 10.0 | 10.0 | 10.0 |
| Specific electric resistance, Ohm/mm, not over | 550×10^{-6} | 600×10^{-6} | 600×10^{-6} | 600×10^{-6} |
| Sodium oxide mass fraction, not over, % | 0.06 | 0.06 | 0.06 | 0.06 |

Disclaimer for Specifications

Every effort is made to ensure that technical specifications are accurate. However, technical specifications included herein should be used as a guideline only and not construed as commitment by any company within or supported by the VALETIME Group. All specifications are subject to change without notice.