

Titanium Dioxide



GRADE R-202

PRODUCT OF THE UKRAINE

This product is from a Valetime Integrated Source

INFORMATION

Standard	TU U 24.1-05766356-054:2005
CAS	13463-67-7 (1317-70-0)
Applications	Titanium Dioxide pigment grade R-202 is used to produce different paintwork materials with good atmosphere resistance, plaster mixtures, plastic, rubber, wall-papers and coloured paper.
Packaging	Valve paper bags 25 kg each on pallets (net weight 1000 kg), disposable PP containers big-bags (net weight 625 kg).

SPECIFICATION

Specification

	<i>Testing methods</i>	<i>Normal</i>
Percentage by weight of Titanium Dioxide, %, min	GOST 9808, p.5.2	93.0
Percentage by weight of rutile form, %, min	GOST 9808, p.5.3	95.0
Percentage by weight of water soluble matters, %, max.	ISO 787/3, ISO 787/8, GOST 21119.2 p.1,2., GOST 9808, p.5.4	0.3
Percentage by weight of volatile matters, %, max.	ISO 787/2, GOST 21119.1, p.2	0.5
pH water suspension	ISO 787/2, GOST 21119.1, p.2	6.5 – 8.0
Residue on the sieve with mesh 0045, %, max.	ISO 787/7, ISO 787/18, GOST 21119.4, p.1, GOST 9808, p.5.7	0.01
Bleaching capability, conventional units, min.	ISO 787/17, GOST 9529, p.2, GOST 9808, p.5.7	1750
Hiding power, g/m ² , max.	GOST 8784, GOST 9808, p.5.8	26
Detachability, mkm, max	ISO 8780-4:1990 (E), GOST 9808, p. 5.9	15
Whiteness, conventional units, min.	ISO 787/1, GOST 9808, p.5.11	93.5
Oil absorption, g/100 g of pigment, max.	ISO 787/5	25.0

Disclaimer for Specifications

Every effort is made to ensure that technical specifications are accurate. However, technical specifications included herein should be used as a guideline only and not construed as commitment by any company within or supported by the VALETIME Group. All specifications are subject to change without notice.